



## HEMPEL'S HI-VEE 56540

<b>Description:</b>	HEMPEL'S HI-VEE 56540 is a non-hiding, but strongly day-light reflecting acrylic paint with fluorescent pigments which give intense colour impression and high visibility (HI-VEE). It has no effect in darkness, and it needs HEMPEL'S HI-VEE LACQUER 06520 on top in order to improve the light fastness.
<b>Recommended use:</b>	For life-saving equipment and for warning purposes such as protruding or moving objects, etc.
<b>Service temperature:</b>	Maximum, dry exposure only: 80°C/176°F see REMARKS overleaf
<b>Availability:</b>	Part of Group Assortment. Local availability subject to confirmation.
<b>PHYSICAL CONSTANTS:</b>	
Shade nos/Colours:	50180*/ Orange
Finish:	Semi-gloss
Volume solids, %:	44 ± 1
Theoretical spreading rate:	11 m <sup>2</sup> /l [441.1 sq.ft./US gallon] to 40 micron/1.6 mils
Flash point:	38 °C [100.4 °F]
Specific gravity:	1 kg/litre [8 lbs/US gallon]
Dry to touch:	1 to 2 hour(s) 20°C/68°F
VOC content:	446 g/l [3.7 lbs/US gallon]

*\*other shades according to assortment list.*

*The physical constants stated are nominal data according to the HEMPEL Group's approved formulas.*

### APPLICATION DETAILS:

Application method:	Airless spray / Air spray / Brush
Thinner (max.vol.):	08230 (5%) / 08230 (15%) / 08230 (5%)
Nozzle orifice:	0.015 to 0.018 "
Nozzle pressure:	150 bar [2175 psi] (Airless spray data are indicative and subject to adjustment)
Cleaning of tools:	HEMPEL'S THINNER 08230
Indicated film thickness, dry:	40 micron [1.6 mils]
Indicated film thickness, wet:	100 micron [4 mils]
Recoat interval, min:	According to specification.
Recoat interval, max:	According to specification.

**Safety:** Handle with care. Before and during use, observe all safety labels on packaging and paint containers, consult HEMPEL Safety Data Sheets and follow all local or national safety regulations.



**HEMPEL'S HI-VEE 56540**

**SURFACE PREPARATION:** According to specification.  
**APPLICATION CONDITIONS:** Apply only on a dry and clean surface with a temperature above the dew point to avoid condensation. In confined spaces provide adequate ventilation during application and drying.

**PRECEDING COAT** According to specification. Recommended systems are: HEMPATEX

**SUBSEQUENT COAT:** HEMPEL'S HI-VEE LACQUER 06520

**REMARKS:**

**Weathering/service temperatures:** Prolonged direct contact at temperatures above approx. 40°C/104°F may cause film indentation.

**Application(s)** Avoid temperature above: 20°C/68°F

**Note:** **HEMPEL'S HI-VEE 56540 For professional use only.**

**ISSUED BY:** HEMPEL A/S

5654050180

This Product Data Sheet supersedes those previously issued.

For explanations, definitions and scope, see "Explanatory Notes" available on [www.hempel.com](http://www.hempel.com). Data, specifications, directions and recommendations given in this data sheet represent only test results or experience obtained under controlled or specially defined circumstances. Their accuracy, completeness or appropriateness under the actual conditions of any intended use of the Products herein must be determined exclusively by the Buyer and/or User.

The Products are supplied and all technical assistance is given subject to HEMPEL's GENERAL CONDITIONS OF SALES, DELIVERY AND SERVICE, unless otherwise expressly agreed in writing. The Manufacturer and Seller disclaim, and Buyer and/or User waive all claims involving, any liability, including but not limited to negligence, except as expressed in said GENERAL CONDITIONS for all results, injury or direct or consequential losses or damages arising from the use of the Products as recommended above, on the overleaf or otherwise. Product data are subject to change without notice and become void five years from the date of issue.